
VAUTID 100T

Wear plate for highly wear resistant hardfacing even at elevated temperatures



VAUTID Material characteristics







Base materials	All weldable steels, mostly boiler plates		
Material type Alloy components	High-chromium/ high-carbon special-alloy on iron base with nickel and manganese additions $C-Cr-Ni-Fe$		
Recommended applications	At high abrasive wear and high temperatures up to 550° C on average corrosion- and impact stress		
Weld deposit properties	Hardness (acc. DIN 32525-4): approx. 700 HV10, 60 HRC*		
Main industries	Metallurgical plant, cement industry, chemical industry, petrochemical industry, etc.		
Typical machine parts	Chutes, sieves, fans, fan housings, cyclones, transfer units, grids, etc.		
Handling	 Conventional machining possible only by grinding Thermal cutting using laser, plasma or water jet cutting Cold working from diameter 300 mm possible with hard facing inside ⁽¹⁾ Cold working from diameter 450 mm possible with hard facing outside ⁽¹⁾ Fixing by welding or bolting on the base material Constructions comparable with conventional steel construction 		

(1) dependent on thickness of plates

Forms of delivery:

Formats (mm)	Thickness of the plates Base material + Hardfacing (mm)	Material Layers	Comments
Standard formats 2.400 x 1.150 ⁽²⁾ 2.900 x 1.400 ⁽²⁾	5+3 ⁽³⁾ , 6+4, 6+6, 8+5, 8+6, 8+8, 10+5, 10+10 Futher combinations on demand	≤ 6 mm: 1 Layer > 6 mm: 2 - 4 Layers	Base material 5 mm: Hardfacing 3 mm Base material 6 mm: Hardfacing 3-6 mm Base material ≥ 8 mm: Hardfacing 3-20 mm
Special body Up to 3.900 x 1.900 ⁽²⁾	On demand	≤ 6 mm: 1 Layer > 6 mm: 2 - 4 Layers	Base material 6 mm: Hardfacing 4-6 mm Base material ≥ 8 mm: Hardfacing 4-20 mm

This data sheet corresponds to the present state of production (October 2016) and can be changed anytime.

(2) Hardfaced area (3) max. 2.900 x 1.400 mm



Hotline: 063-271-9119 E-Mail: sales@varakana.com

Website: www.vautidthailand.com

^{*} subject to common industrial fluctuations